

# Corro-Shield International, Inc.

10548 Lunt Avenue, Rosemont, IL 60018 • 847/298-7770 • 847/298-7784 fax

## PRODUCT DATA SHEET (Rev. 7/00)

### CORRO-GROUT (Ref. No. 400)

#### Product Description

- Unique Epoxy System for Bedding and Grouting
- Supplied in Either Bricklayers or Tilesetters Grout
- Grouting for Acid Brick or Tile to Floors and Walls
- Supplied With Clear Resin and Colored Aggregate
- 100% Solids Epoxy Resin
- Self-Priming, Resin-Rich
- U.S.D.A. Approved/V.O.C. Compliant
- Low Odor/Solvent Free

#### Special Features

- Meets ASTM C-884  
Thermal Compatibility with Concrete
- Excellent Adhesion to Clean, Sound, Damp Concrete
- Excellent Adhesion to Brick and Tile
- Color Stable Grout
- Resin Rich Surface Helps to Resist Bacterial Growth
- Less Than .01% Absorption
- Resilient to Compensate for Tile "Creep"
- Holds its Peak When Applied With a Notched Trowel
- Excellent Adhesion to 24 Hour Old Concrete by First Priming with **Corro-Cure**
- Resistant to Many Acids, Solvents and Cleaning Solutions. (Refer to Chemical Resistance Chart)
- For Grouting to Walls, add Corro-Thickener
- Built in Resiliency for Thermal Shock (Steam Cleaning) and Impact Resistance
- Can be Used Indoors or Outdoors
- User Friendly Mix Ratio
- Water Wipeable
- Hygienic, Easy to Clean Surface

#### Application

- Breweries, Beverage Industry, Meat Packing and Poultry Plants, Dairies, Food Processing Plants, Bakeries, Chemical Plants, Pharmaceutical Plants, Distribution Centers and Warehouses

#### Packaging

One Gallon Pak –Pre--Measured  
Standard Pak – 3 Gallon Pak Pre-Measured  
Ten Pak – 10 x 3 Gallon Pre-Measured Paks  
80 Gallon Bulk Pak – Provided in Bulk with Measuring Pails

#### Bedding

**Corro-GROUT** liquids, when mixed with our Tilesetters Corro-Fill, makes an excellent bedding compound that holds its peak when applied with a notched trowel (Ref. No. 400 BG). For grouting of wall tiles, add Corro-Thickener.

#### Priming

**Corro-GROUT** is resin-rich and does not need a primer on "good" concrete. For deteriorated concrete, priming will help reduce outgassing, blistering, and dry spots. Refer to **Corro-Prime** data sheet. If the **Corro-GROUT** is going to be applied over "green" concrete, then our **Corro-Cure** (a slow set primer) must be used first.

#### Set Times

**Corro-GROUT** is available in various setting times. For quick reference, the following guide is given for the different temperature applications:

**Corro-GROUT** For ambient or higher temperatures.

**Corro-GROUT F.S. (Fast Set)** For faster set times at ambient or higher temperatures.

**Corro-GROUT-X.F.S. (Extra Fast Set)** - For extremely fast set times at ambient or higher temperatures.

**Corro-GROUT C.S. (Cold Set)** – For application temperatures from 45°F. and higher.

**Corro-GROUT X.C.S. (Extra Cold Set)** - For application temperatures from 35°F. and higher.

Applications below 35°F please consult the factory.

**See Set Time Chart for various setting times.**

#### Mixing and Application

Detailed mixing and application instructions are available upon request.

#### Colors

Neutral, Black, White, Gray, Dark Gray, Brick Red, Beige, Green and Brown. Special colors are available upon request, for an additional charge.

#### Clean Up

**Corro-GROUT** while still wet can be cleaned up with warm soapy water, but if allowed to set then mechanical cleaning or the application of a very strong paint stripper will have to be used.

#### Precautions

As with all epoxies, good hygienic habits must be observed and the wearing of protective clothing and gloves is advised. Before using any of the products, please read their respective safety data sheets.

#### Technical Assistance

If you have any questions regarding this product, please call 1-800/298-7637 for further information.

## Corro-Grout Product Data Sheet - Page 2

Density (lbs./gallon) = 13.45

Mixing Ratio By Volume

Part A: Part B: 2:1     A & B Mixed: Corro-Fill: 1:2

Approximate Bedding Coverage Per Gallon

1/8" Thick = 12.8 SF     1/4" Thick = 6.4 SF

Approximate Coverage Per Gallon for Jointing for Brick or Tile

Brick/Tile Size	Joint Width	Square Foot Coverage
4" x 8" x 1/2"	1/8"	70
	1/4"	35
4" x 8" x 1 3/8"	1/8"	25
	1/4"	12.5

<b>Set Times (Slab Temperature)</b>	<b>50°F.</b>	<b>73°F.</b>	<b>90°F.</b>
Pot Life	1 Hour	45 Minutes	25 Minutes
Foot Traffic	18 Hours	15 Hours	12 Hours
Forklift Traffic	72 Hours	48 Hours	24 Hours
Full Chemical Resistance*	9 Days	7 Days	5 Days

\*Refer to Chemical Resistance Chart

ASTM	TEST METHOD	Liquids Only	Filled System
C579	Compressive Strength		5083 psi
C579	Percent Compressive Resiliency		3.68%
	<b>Ratio of Force to % Resiliency</b>		1381:1
C579	Compressive Strength @ Yield		4092 psi
C579	Percent Compressive Resiliency @ Yield		2.18%
D695	Compressive Strength	7373 psi	
D695	Percent Compressive Resiliency	47.18%	
	<b>Ratio of Force to % Resiliency</b>	156:1	
D695	Compressive Strength @ Yield	3319 psi	
D695	Percent Compressive Resiliency @ Yield	9.66%	
C580	Flexural Strength		2959 psi
C580	Flexural Modulus of Elasticity		6.08 x 10 <sup>5</sup>
D790	Flexural Strength	4800 psi	
D790	Flexural Modulus of Elasticity	1.73 x 10 <sup>5</sup>	
C307	Tensile Strength		1446 psi
C307	Percent Tensile Elongation		6.75%
	<b>Ratio of Tensile Stress to % Elongation</b>		214:1
D638	Tensile Strength	1993 psi	
D638	Percent Tensile Elongation	18%	
	<b>Ratio of Tensile Stress to % Elongation</b>	111:1	
C321	Bond Strength to Concrete		Failure in Concrete
D4541	Bond Strength to Concrete	Failure in Concrete	
C884	Thermal Compatibility to Concrete	No Delamination	No Delamination
C413	Absorption Filled		Less Than .1%
C413	Absorption Unfilled	0%	

**WARRANTY**

The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerable uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

**WARRANTY** - All products manufactured by us are warranted to be first class material and free from defects in material and workmanship.

Liability under this warranty is limited to the net purchase price of any such products proven defective, or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims hereunder on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other materials and products. WE MAKE NO WARRANTY, EXPRESS OR IMPLIED, AS TO THE SUITABILITY OF ANY OF OUR PRODUCTS FOR ANY PARTICULAR USE, AND WE SHALL NOT BE SUBJECT TO LIABILITY FROM ANY DAMAGES RESULTING FROM THEIR USE IN OPERATIONS NOT UNDER OUR DIRECT CONTROL.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF OURS OR ANY OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS.