

Corro-Shield International, Inc.

10548 Lunt Avenue, Rosemont, IL 60018 • 847/298-7770 • 847/298-7784 fax

PRODUCT DATA SHEET (Rev. 1/00)

CORRO ULTRA-GROUT (Ref. No. 402)

Product Description

- Unique Epoxy System for Bedding and Grouting
- Supplied in Either Bricklayers or Tilers Method
- Grouting for Acid Brick or Tile to Floors and Walls
- Supplied With Clear Resin and Colored Aggregate
- 100% Solids Epoxy Resin
- Self-Priming, Resin-Rich
- U.S.D.A. Compliant/V.O.C. Compliant
- Low Odor/Solvent Free

Special Features

- Meets ASTM C-884 Thermal Compatibility with Concrete
- Excellent Adhesion to Clean, Sound, Damp Concrete
- Excellent Adhesion to Brick and Tile
- Color Stable Grout
- Resin Rich Surface Helps to Resist Bacterial Growth
- Less Than .01% Absorption
- Resilient to Compensate for Tile "Creep"
- Holds its Peak When Applied With a Notched Trowel
- Resistant to Many Acids, Solvents and Cleaning Solutions, Including Methylene Chloride. (Refer to Chemical Resistance Chart)
- For Grouting to Walls, add Corro-Thickener
- Built in Resiliency for Thermal Shock (Steam Cleaning) and Impact Resistance
- Can be Used Indoors or Outdoors
- User Friendly Mix Ratio
- Water Wipeable
- Hygienic, Easy to Clean Surface

Application

- Breweries, Beverage Industry, Meat Packing and Poultry Plants, Dairies, Food Processing Plants, Bakeries, Chemical Plants, Pharmaceutical Plants, Distribution Centers and Warehouses

Packaging

One Gallon Pak –Pre--Measured
Standard Pak – 3 Gallon Pak Pre-Measured
Ten Pak – 10 x 3 Gallon Pre-Measured Paks
80 Gallon Bulk Pak – Provided in Bulk with Measuring Pails

Bedding

Corro Ultra-GROUT liquids, when mixed with our Tilers Corro-Fill, makes an excellent bedding compound that holds its peak when applied with a notched trowel (Ref. No. 402 BG). For grouting of wall tiles, add Corro-Thickener.

Priming

Corro Ultra-GROUT is self-priming, however, priming with **Corro Ultra-Prime** is recommended only as a precautionary measure to try and seal the concrete to help reduce outgassing and eliminate the formation of blisters and "dry spots". Do not use any other primer. Refer to **Corro Ultra-Prime** data sheet.

Set Times

Corro Ultra-GROUT is only available in one setting time, and should be applied at temperatures between 50°F and 90°F. For various set times, see back page. For temperatures lower than 50°F., please consult the factory.

Mixing and Application

Detailed mixing and application instructions are available upon request.

Colors

Neutral, Black, White, Gray, Dark Gray, Brick Red, Beige, Green and Brown. Special colors are available upon request, for an additional charge.

Clean Up

Corro Ultra-GROUT while still wet can be cleaned up with warm soapy water, but if allowed to set then mechanical cleaning or the application of a very strong paint stripper will have to be used.

Precautions

As with all epoxies, good hygienic habits must be observed and the wearing of protective clothing and gloves is advised. Before using any of the products, please read their respective safety data sheets.

Technical Assistance

If you have any questions regarding this product, please call 1-800/298-7637 for further information.

Corro Ultra-Grout Product Data Sheet - Page 2

Density (lbs./gallon) = 13.47

Mixing Ratio By Volume

Part A: Part B: 2:1 A & B Mixed: Corro-Fill: 1:3

Approximate Bedding Coverage Per Gallon

1/8" Thick = 12.8 SF 1/4" Thick = 6.4 SF

Approximate Coverage Per Gallon for Jointing of Brick or Tile

<u>Brick/Tile Size</u>	<u>Joint Width</u>	<u>Square Foot Coverage</u>
4" x 8" x 1/2"	1/8"	70
	1/4"	35
4" x 8" x 1 3/8"	1/8"	25
	1/4"	12.5

<u>Set Times (Slab Temperature)</u>	<u>50°F.</u>	<u>73°F.</u>	<u>90°F.</u>
Pot Life	40 Minutes	20 Minutes	15 Minutes
Foot Traffic	12 Hours	4 Hours	2 Hours
Forklift Traffic	36 Hours	24 Hours	12 Hours
Full Chemical Resistance	9 Days	7 Days	5 Days

<u>ASTM</u>	<u>TEST METHOD</u>	<u>Liquids Only</u>	<u>Filled System</u>
C579	Compressive Strength		8467 psi
C579	Compressive Resiliency		11.76%
	Ratio of Force to % Resiliency		720:1
C579	Compressive Strength @ Yield		4300 psi
C579	Compressive Resiliency @ Yield		3%
D695	Compressive Strength	7738 psi	
D695	Compressive Resiliency	26.8%	
	Ratio of Force to % Resiliency	289:1	
D695	Compressive Strength @ Yield	5017 psi	
D695	Compressive Resiliency @ Yield	7.9%	
C580	Flexural Strength		5060 psi
C580	Flexural Modulus of Elasticity		8.88 x 10 ⁵
D790	Flexural Strength	1200 psi	
D790	Flexural Modulus of Elasticity	2.04 x 10 ⁵	
C307	Tensile Strength		2450 psi
C307	Tensile Elongation		9.95%
	Ratio of Stress to % Elongation		246:1
D638	Tensile Strength	4420 psi	
D638	Tensile Elongation	12.74%	
	Ratio of Stress to % Elongation	347:1	
C321	Bond Strength to Concrete	Failure in Concrete	
D4541	Bond Strength to Concrete		Failure in Concrete
C884	Thermal Compatibility to Concrete	No Delamination	No Delamination
C413	Absorption Filled		Less Than .01%
C413	Absorption Unfilled	Less Than .01%	

WARRANTY

The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerable uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

WARRANTY - All products manufactured by us are warranted to be first class material and free from defects in material and workmanship.

Liability under this warranty is limited to the net purchase price of any such products proven defective, or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims hereunder on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other materials and products. WE MAKE NO WARRANTY, EXPRESS OR IMPLIED, AS TO THE SUITABILITY OF ANY OF OUR PRODUCTS FOR ANY PARTICULAR USE, AND WE SHALL NOT BE SUBJECT TO LIABILITY FROM ANY DAMAGES RESULTING FROM THEIR USE IN OPERATIONS NOT UNDER OUR DIRECT CONTROL.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF OURS OR ANY OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS.